Università degli Studi di Padova

Padua Research Archive - Institutional Repository

Transient self-assembly of molecular nanostructures driven by chemical fuels

Original Citation:

Availability:

This version is available at: 11577/3227880 since: 2017-05-16T08:55:37Z

Publisher:

Elsevier Ltd

Published version:

DOI: 10.1016/j.copbio.2016.10.014

Terms of use:

Open Access

This article is made available under terms and conditions applicable to Open Access Guidelines, as described at <http://www.unipd.it/download/file/fid/55401> (Italian only)

(Article begins on next page)

Dear author,

Please note that changes made in the online proofing system will be added to the article before publication but are not reflected in this PDF.

We also ask that this file not be used for submitting corrections.

ELSEVIER

Available online at www.sciencedirect.com

ScienceDirect

Current Opinion in
Biotechnology

Transient self-assembly of molecular nanostructures driven by chemical fuels

Flavio della Sala^{*}, Simona Neri^{*}, Subhabrata Maiti, Jack L-Y Chen and Leonard J Prins

Over the past decades, chemists have mastered the art of assembling small molecules into complex nanostructures using non-covalent interactions. The driving force for self-assembly is thermodynamics: the self-assembled structure is more stable than the separate components. However, biological self-assembly processes are often energetically uphill and require the consumption of chemical energy. This allows nature to control the activation and duration of chemical functions associated to the assembled state. Synthetic chemical systems that operate in the same way are essential for creating the next generation of intelligent, adaptive materials, nanomachines and delivery systems. This review focuses on synthetic molecular nanostructures which assemble under dissipative conditions. The chemical function associated to the transient assemblies is operational as long as chemical fuel is present.

Address

Department of Chemical Sciences, University of Padova, Padova, Italy

Corresponding author: Prins, Leonard J (leonard.prins@unipd.it)

^{*} These authors contributed equally.

Current Opinion in Biotechnology 2017, 46:xx–yy

This review comes from a themed issue on **Nanobiotechnology**

Edited by **Ben Davis** and **Christopher Serpell**

<http://dx.doi.org/10.1016/j.copbio.2016.10.014>

0958-1669/© 2016 Elsevier Ltd. All rights reserved.

Introduction

Over the past decades self-assembly has emerged as the most powerful strategy for the formation of molecular nanostructures. It has permitted the development of innovative systems for diagnostics and catalysis and has enabled enormous advances in the fields of materials chemistry and nanotechnology [1]. Although inspired by nature, there is a strong current awareness that nature is only mimicked to a certain extent [2^{*}]. While many biological self-assembly processes are driven by thermodynamics [3], just as in synthetic self-assembly, there are also situations in which self-assembly is associated with an energy consumption process, referred to as dissipative

self-assembly [4,5]. Nature exploits dissipative self-assembly as a way to obtain temporal control over the chemical functions associated with the assembled state [6–10]. There is currently a strong drive to implement the same principle also in synthetic systems, with the ultimate aim of creating intelligent materials and devices able to perform different functions based on the stimuli provided in the form of energy [11,12,13^{*},14–20]. In the last years this has led to the development of various chemical systems that require energy to self-assemble into functional structures. Most frequently, energy is provided in the form of physical stimuli, mainly as light [16,21–27], but also as ultrasound [28], electrical current [29], osmotic pressure [30] or, alternatively, by (transiently) changing the pH [31,32]. This is highly attractive, because this energy can be delivered in a clean manner to the system and is consumed without the creation of waste. However, nature predominantly exploits chemical energy as a trigger for the selective activation of function. The design of synthetic systems that rely on chemical fuels for self-assembly is challenging and has mainly focused on the development of hybrid structures in which natural dissipative systems, such as microtubules, are conjugated with synthetic elements such as nanoparticles [33–38]. Another successful approach relies on the coupling of a self-assembly process to a chemical oscillator, such as the Belousov–Zhabotinsky (BZ) reaction, which operates intrinsically out-of-equilibrium [39–43]. However, although functional, these systems do not provide much flexibility since the energy dissipation process is extremely well-defined and difficult to modulate [44^{*}]. The scope of this short review is to highlight recent advances made in the design of synthetic molecular assemblies that require chemical fuels to be functional. It will be shown that such systems maintain the assembled state only as long as chemical fuel is present. The result is that the chemical functions exerted by the assemblies have a transient character.

Soft materials

The first step towards artificial systems able to mimic the transient nature of microtubule-formation was reported by Van Esch *et al.* [45^{**}]. Their approach was based on dibenzoyl-L-cystine (DBC), which is a pH-responsive gelator (Figure 1a). Above the pK_a-value of the carboxylic acids (around 4.5) gel formation does not occur, because of electrostatic repulsion between the carboxylate groups. Protonation of the carboxylic groups at pH-values below

Figure 1

Transient gel formation relying on (a) the rapid esterification of the pro-gelator DBC or (b) the rapid formation of a dipeptide hydrogelators under hydrolytic conditions.

the pK_a results in neutralization and consequent self-assembly of the molecule in long fibers, stabilized by intermolecular hydrogen-bonding. On the other hand, the corresponding DBC-diester (DBC-(OMe)₂) assembles at all pH-values, even above the pK_a . The properties of these molecules were used to design a dissipative cycle in which methyl-iodide (MeI) was used to methylate DBC under ambient conditions (35°C). Under these conditions a spontaneous hydrolysis of the formed esters also took place leading to a return to the starting compound, which crucially was at a rate that is lower than that of ester formation. This implies that the addition of MeI leads to the transient presence of the gelator DBC-(OMe)₂ in the system, with a lifetime that depends on the amount of fuel added. Transient gel formation was confirmed by light scattering studies and scanning electron microscopy (SEM). Confirmation that the system returned to the original state was demonstrated by the observation that the addition of a new batch of MeI induced a second cycle of transient gel formation. This first system suffered from relatively long response times with life-cycles in the order of days. In a follow-up study, the life times could be reduced to hours by changing the chemical fuel and optimizing the pH level [46]. However, the importance of this study lays in the demonstration that the

mechanical properties of the gel could be controlled by the initial level of the chemical fuel. The addition of low concentrations of MeI resulted in short-lived weak gels, whereas long-lived stiff gels were obtained at high concentrations of fuel. Furthermore, it was also shown that these materials had a much higher capacity for self-regeneration after destruction when high fuel levels were present.

Debnath *et al.* developed an alternative hybrid biosynthetic system for transient gel formation which relied on the gelating properties of naphthalene-dipeptides and the ability of enzymes to form and cleave peptide bonds (Figure 1b) [47]. Starting point was the α-chymotrypsin catalyzed transacylation of a series of hydrophobic amino acids X-NH₂ (with X = Y, F or L) using Nap-Y-OMe as an acyl-donor which rapidly yielded the dipeptide hydrogelator Nap-YX-NH₂. However, in time α-chymotrypsin caused the installment of an equilibrium between the hydrogelator Nap-YX-NH₂ and the hydrolysis products Nap-Y-OH and the original amino acid X-NH₂ leading to a constant equilibrium concentration of the gelator. When F-NH₂ was used, the final concentration of Nap-YF-NH₂ was above the critical gelation concentration (CGC) leading to the formation of a stable gel. On the other hand,

transient gel formation was observed when amino acids Y-NH₂ and L-NH₂ were used, as the concentration of the dipeptide in these systems remained only for a limited time above the CGC. The lifetime of these gels could be tuned by changing the pH. It was shown that the system could be refueled up to three times by adding additional equivalents of Nap-Y-OMe. After three cycles the system was no longer able to reach the dipeptide-concentrations required to reach the CGC, presumably because of interference with the accumulating amounts of the waste product Nap-Y-OH in the system.

This approach was then extended to a system of tripeptide-gelators in which structurally diverse amino acids were ligated in an analogous manner to aspartame, a DF-dipeptide methylester [48]. Only for F-NH₂ and Y-NH₂ transient gel formation was observed; in the presence of amino acids W, L, V, S and T, no gelation was observed. For the latter amino acids, rapid formation of the end product DF-OH was seen. Hardly any formation of the tripeptide was observed, despite the fact that some of these amino acids (L, V, S) were used as effective nucleophiles in previous studies. The observation of gel formation for F and Y suggests that these transient nanofibers are less prone to enzymatic hydrolysis and thus permit conditions for transient structure formation (rate_{formation} > rate_{destruction}). Interestingly, while the DFF-NH₂ peptide turned out to be thermodynamically more stable compared to DFY-NH₂, direct competition experiments revealed that the selection in this system relied on kinetic control, yielding DFY-NH₂ as the major product.

An alternative biocatalytic approach towards transient hydrogel formation relied on the sucrose-fueled production of CO₂ by yeast [49]. Acidification of an aqueous solution upon the dissolution of CO₂ resulted in the protonation of a peptide-based surfactant causing the formation of a gel. Gradual elimination of CO₂ from the system upon evaporation resulted in spontaneous return to the original state.

A different approach towards transient polymer self-assembly was developed by Kumar *et al.* and relies on the exploitation of naphthalenediimide chromophores appended with Zn(II)-complexes [50]. Whereas the building block by itself showed no signs of aggregation, the addition of adenosine phosphates (AXP with X = M, D, or T) resulted in the formation of helical stacks with the anionic AXPs lined up against the outward-pointing cationic side-groups [51]. Interestingly, it was observed that the handedness of the supramolecular polymer depended on the nature of the adenosine phosphate. This provided an important tool to follow the spontaneous transition of the structures across the supramolecular energy landscape upon the enzyme-catalysed hydrolysis of ATP → ADP → AMP → P_i. The system is in

principle amenable to repetitive cycles by displacing P_i with the high-affinity binder ATP under dissipative conditions.

Nanostructures

Surfactant-based systems

The self-assembly of surfactants into large structures, such as micelles and vesicles, has always attracted great interest because of the similarity of these structures to cells and also for their numerous practical applications [52]. The functional properties of these systems mainly originate from the presence of an internal compartment that is separated from the bulk and from the presence of an apolar phase in aqueous media. Methodology to control the formation of these systems through the addition of chemical fuel under dissipative conditions would give temporal control over their associated functions. As illustration, Wang *et al.* coupled the formation of supra-amphiphiles to the chemical oscillator IO₃[−]-NH₃OH⁺-OH[−] which periodically generates iodine [53]. Reaction of iodine with the PEG segment of a hydrophilic block copolymer increased the hydrophobicity of that domain and induced its self-assembly into supra-amphiphiles. The oscillating concentration of iodine caused spontaneous transitions between assembled and dissociated states as a function over time. Although not surfactant-based, the system nicely illustrates the possibility to regulate the self-assembly process in time using a chemical fuel. The following examples illustrate how this can be used to control the chemical functions associated with the assembled state.

Our group developed a strategy for the transient stabilization of vesicular aggregates (Figure 2a) [54^{••}] based on a previous study aimed at transient signal generation by a nanoparticle-based system [55]. A surfactant containing a cationic 1,4,7-triazacyclononane (TACN)-Zn(II) head group was found to form micellar aggregates with a critical micelle concentration (CMC) of around 100 μM. However, the presence of ATP resulted in the formation of vesicular aggregates at much lower concentrations. This is attributed to the stabilizing interactions between ATP and the oppositely charged head groups, which also causes a repositioning of the surfactants. Importantly, previous studies using monolayer protected gold nanoparticles containing identical head groups had demonstrated a strong dependence between the number of negative charges present in a series of adenosine phosphates (AXP with X = M, D, or T) and the affinity for the multivalent surface [55]. The incapacity of AMP to stabilize aggregates below the cmc was then exploited for the transient self-assembly of vesicular aggregates. ATP was added to surfactants at concentrations below the cmc in the presence of potato apyrase, which is an enzyme that hydrolyses ATP into AMP + 2P_i. Since the rate of aggregate formation induced by ATP is more rapid than the decay rate of

Figure 2

(a) The transient formation of vesicles driven by ATP and (b) the transient formation of membrane channels driven by the activation of precursor A.

ATP, a transient period exists in which aggregates are formed. Upon depletion of ATP, the system spontaneously reverted to the non-aggregated state, which was confirmed by a series of techniques which included DLS, UV-vis, fluorescence and confocal microscopy. The process of transient aggregate formation could be repeated multiple times upon the addition of new batches of ATP. Next, this process was coupled to a chemical reaction that was strongly favored by the apolar bilayer of the aggregates. It was shown that the lifetime of the vesicles determined the amount of reaction product formed by the system. Thus this system provides a new means to indirectly control the outcome of a chemical reaction through the exploitation of a transient phenomenon driven by a chemical fuel.

The group of Fyles described the transient formation of channels in a membrane system driven by a chemical fuel (Figure 2b) [56*]. The project was based on the knowledge that compounds analogous to **C** are able to span a bilayer membrane and create a hydrophilic pore able to translocate ions across the membrane. The key novel feature of molecule **C** is the presence of a labile thioester-bond. In the absence of the acyl part (such as in **A**), channel activity was not observed and this represents the inactive resting state. Upon the addition of thioester **B** as a chemical fuel, thiol-thioester exchange occurs spontaneously leading to

the *in situ* formation of the channel-forming compound **C**. Channel activity was measured using the voltage-clamp technique which measures changes in conductivity upon the transport of ions across the membrane [57]. Importantly, compound **C** is terminated with a nucleophilic amine, which is able to intramolecularly attack the thioester bond leading to the spontaneous re-formation of the resting compound **A** and the cyclic waste product **D**. The rate of the intramolecular reaction can be tuned by changing the spacer length separating the amine and the carbonyl-group of the thioester-bond. Transient accumulation of the pore-forming compound **C** occurs if the intramolecular cyclization-rate is slower than the transthioesterification reaction. Time-dependent conductance measurements confirmed the spontaneous decrease in pore-activity, which could be regenerated upon the addition of a fresh batch of fuel. It is noted that this system is intrinsically dissipative in the sense that formation of the active compound automatically installs a mechanism of self-destruction because of the presence of the nucleophile. This makes it different from most other systems discussed here, that rely on the creation of dissipative conditions by external elements (such as enzymes or bases). The ability to tune the efficacy of the intramolecular reaction and thus control the dissipative process illustrates the advantages and potential of synthetic systems.

Molecular cages

The first examples are appearing in which the self-assembly of molecularly well-defined structures is governed by the transient action of chemical fuels. Wood *et al.* reported a self-assembled cage composed of porphyrin building blocks and Cu(I)-metal ions that dissociate upon the addition of triphenylphosphine (PPh₃) [58[•]]. This is because of the preferential formation of heteroleptic N, P-complexes with Cu(I) (Figure 3a). However, when PPh₃ is added under oxidative conditions (because of the presence of pyridine *N*-oxide as an oxidant and the *oxo*-transfer catalyst ReCat as an accelerator), it is slowly converted to triphenylphosphine oxide which no longer coordinates Cu(I). Consequently, the system reverts back to the assembled state. A new cycle can be initiated by adding a new batch of PPh₃. Transient dissociation of the cage occurs because the oxidation rate is much lower compared to rate of the ligand exchange. A hint of a possible application as delivery agent was provided by demonstrating the transient release of an encapsulated C₆₀-guest upon the addition of fuel.

Finally, a very intriguing example was reported by Fanlo-Virgos *et al.* which described the transient adaptation of a dynamic molecular network to the addition of a guest (Figure 3b) [59^{••}]. A library of very diverse molecular structures including catenanes and tetramers was spontaneously formed upon the partial oxidation of a building

block containing two thiol moieties. The reversibility of the disulfide bond permitted interconversion between the library members and imparted adaptability to the network. A remarkable spontaneous shift in the library composition towards the tetrameric species was observed upon the addition of compound **E** ascribed to the installment of favorable interactions between the tetramers and compound **E**. In the absence of other events this would just have been an example of guest-induced templated synthesis, but in this particular case it was observed that in time the system spontaneously returned to the original composition. It turned out that the tetramers catalyze the conversion of compound **E** into product **F** and dimethylamine through an *aza*-Cope rearrangement. The fact that a second addition of guest induces a new transient shift in library composition confirms the reversibility of the process and demonstrates the capacity of the system to spontaneously dissipate the energy provided by the guest. Like the transmembrane pore-formation discussed above, also this system is intrinsically dissipative. The exciting prospect offered by these results is the development of dynamic networks that are able to transiently evolve into different directions depending on the input of chemical information.

Outlook

Compared to traditional self-assembly processes which rely on the installment of a functional thermodynamically

Figure 3

(a) Transient displacement of fullerene from a molecular cage driven by triphenylphosphine and (b) transient adaptation of a molecular network to a substrate.

6 Nanobiotechnology

stable state, the key novelty introduced by performing self-assembly under dissipative conditions is that control can be gained over the lifetime of the chemical function associated with the assembled state. Energy can also be delivered using a variety of physical means, but the use of chemical fuels brings us one step closer to mimicking biological networks that mostly rely on fluxes of energy stored in molecules. The examples presented here are still rather primitive and in most cases dissipative conditions are artificially created by the addition of an external component (catalyst, enzyme, reagent) to the system that dissipates the energy stored in the fuel. Yet, some of the systems discussed are intrinsically dissipative, implying that it is the self-assembled structure itself that causes energy dissipation. One further step up the ladder is the design of structures that assemble as a result of energy dissipation. The ability to use time as a regulatory element in designing chemical systems offers new and exciting possibilities for the design of reaction networks, functional materials and delivery systems.

Acknowledgement

Financial support from the EU Horizon 2020 programme (MSCA642793 and 657486) is acknowledged.

References and recommended reading

Papers of particular interest, published within the period of review, have been highlighted as:

- of special interest
- of outstanding interest

1. Gale PA, Steed JW (Eds): *Self-assembly and Supramolecular Devices (Supramolecular Chemistry: From Molecules to Nanomaterials)*, vol. 5. Wiley; 2012.
2. Whitesides GM, Grzybowski B: **Self-assembly at all scales.** *Science* 2002, **295**:2418–2421.
This review provides an excellent overview of the importance of self-assembly in different fields and sets the stage for the design of synthetic self-assembly processes beyond those driven by thermodynamics.
3. Kushner DJ: **Self-assembly of biological structures.** *Bacteriol Rev* 1969, **33**:302–245.
4. Karsenti E: **Self-organization in cell biology: a brief history.** *Nat Rev Mol Cell Biol* 2008, **9**:255–262.
5. Fialkowski M, Bishop KJM, Klajn R, Smoukov SK, Campbell CJ, Grzybowski BA: **Principles and implementations of dissipative (dynamic) self-assembly.** *J Phys Chem B* 2006, **110**:2482–2496.
6. Nicolis G, Prigogine I: *Self-organization in Non-equilibrium Systems: From Dissipative Structures to Order Through Fluctuations*. Wiley; 1977.
7. Desai A, Mitchison TJ: **Microtubule polymerization dynamics.** *Annu Rev Cell Dev Biol* 1997, **13**:83–117.
8. Howard J: *Mechanics of Motor Proteins and the Cytoskeleton*. Sunderland, MA: Sinauer Associates, Inc.; 2001.
9. Saibil H: **Chaperone machines for protein folding, unfolding and disaggregation.** *Nat Rev Mol Cell Biol* 2013, **14**:630–642.
10. Rizzoli SO: **Synaptic vesicle recycling: steps and principles.** *EMBO J* 2014, **33**:788–822.
11. Mann S: **Self-assembly and transformation of hybrid nano-objects and nanostructures under equilibrium and non-equilibrium conditions.** *Nat Mater* 2009, **8**:781–792.
12. Warren SC, Guney-Altay O, Grzybowski BA: **Responsive and nonequilibrium nanomaterials.** *J Phys Chem Lett* 2012, **3**:2103–2111.
13. Mattia E, Otto S: **Supramolecular systems chemistry.** *Nat Nanotechnol* 2015, **10**:111–119.
This review describes the recent progress in shifting the field of supramolecular chemistry based on thermodynamics towards the field of systems chemistry relying on energy dissipation.
14. Grzybowski BA, Huck WTS: **The nanotechnology of life-inspired systems.** *Nat Nanotechnol* 2016, **11**:584–591.
15. Le Saux T, Plasson R, Jullien L: **Energy propagation throughout chemical networks.** *Chem Commun* 2014, **50**:6189–6195.
16. Ragazzon G, Baroncini M, Silvi S, Venturi M, Credi A: **Light-powered autonomous and directional molecular motion of a dissipative self-assembling system.** *Nat Nanotechnol* 2015, **10**:70–75.
17. Cheng CY, McGonigal PR, Schneebeli ST, Li H, Vermeulen NA, Ke CF, Stoddart JF: **An artificial molecular pump.** *Nat Nanotechnol* 2015, **10**:547–553.
18. Cheng CY, McGonigal PR, Liu WG, Li H, Vermeulen NA, Ke CF, Frasconi M, Stern CL, Goddard WA, Stoddart JF: **Energetically demanding transport in a supramolecular assembly.** *J Am Chem Soc* 2014, **136**:14702–14705.
19. Wilson MR, Sola J, Carlone A, Goldup SM, Lebrasseur N, Leigh DA: **An autonomous chemically fuelled small-molecule motor.** *Nature* 2016, **534**:235–240.
20. Collins BSL, Kistemaker JCM, Otten E, Feringa BL: **A chemically powered unidirectional rotary molecular motor based on a palladium redox cycle.** *Nat Chem* 2016, **8**:860–866.
21. Klajn R, Bishop KJM, Grzybowski BA: **Light-controlled self-assembly of reversible and irreversible nanoparticle suprastructures.** *Proc Natl Acad Sci U S A* 2007, **104**:10305–10309.
22. Klajn R, Wesson PJ, Bishop KJM, Grzybowski BA: **Writing self-erasing images using metastable nanoparticle “Inks”.** *Angew Chem Int Ed* 2009, **48**:7035–7039.
23. Soejima T, Morikawa M, Kimizuka N: **Holey gold nanowires formed by photoconversion of dissipative nanostructures emerged at the aqueous-organic interface.** *Small* 2009, **5**:2043–2047.
24. Palacci J, Sacanna S, Steinberg AP, Pine DJ, Chaikin PM: **Living crystals of light-activated colloidal surfers.** *Science* 2013, **339**:936–940.
25. Ito S, Yamauchi H, Tamura M, Hidaka S, Hattori H, Hamada T, Nishida K, Tokonami S, Itoh T, Miyasaka H et al.: **Selective optical assembly of highly uniform nanoparticles by doughnut-shaped beams.** *Sci Rep* 2013, **3**:3047.
26. Zhao H, Sen S, Udayabhaskararao T, Sawczyk M, Kucanda K, Manna D, Kundu PK, Lee JW, Kral P, Klajn R: **Reversible trapping and reaction acceleration within dynamically self-assembling nanoflasks.** *Nat Nanotechnol* 2016, **11**:82–88.
27. Ikegami T, Kageyama Y, Obara K, Takeda S: **Dissipative and autonomous square-wave self-oscillation of a macroscopic hybrid self-assembly under continuous light irradiation.** *Angew Chem Int Ed* 2016, **55**:8239–8243.
28. Pappas CG, Mutasa T, Frederix P, Fleming S, Bai S, Debnath S, Kelly SM, Gachagan A, Ulijn RV: **Transient supramolecular reconfiguration of peptide nanostructures using ultrasound.** *Mater Horiz* 2015, **2**:198–202.
29. Krabbenborg SO, Veerbeek J, Huskens J: **Spatially controlled out-of-equilibrium host-guest system under electrochemical control.** *Chem Eur J* 2015, **21**:9638–9644.
30. Rikken RSM, Engelkamp H, Nolte RJM, Maan JC, van Hest JCM, Wilson DA, Christianen PCM: **Shaping polymersomes into predictable morphologies via out-of-equilibrium self-assembly.** *Nat Commun* 2016, **7**:12606.

31. Heuser T, Steppert AK, Lopez CM, Zhu BL, Walther A: **Generic concept to program the time domain of self-assemblies with a self-regulation mechanism.** *Nano Lett* 2015, **15**:2213-2219.
32. Heuser T, Weyandt E, Walther A: **Biocatalytic feedback-driven temporal programming of self-regulating peptide hydrogels.** *Angew Chem Int Ed* 2015, **54**:13258-13262.
33. Kakugo A, Sugimoto S, Gong JP, Osada Y: **Gel machines constructed from chemically cross-linked actins and myosins.** *Adv Mater* 2002, **14**:1124-1126.
34. Hess H, Clemmens J, Brunner C, Doot R, Luna S, Ernst KH, Vogel V: **Molecular self-assembly of “nanowires” and “nanospools” using active transport.** *Nano Lett* 2005, **5**:629-633.
35. Liu HQ, Spoerke ED, Bachand M, Koch SJ, Bunker BC, Bachand GD: **Biomolecular motor-powered self-assembly of dissipative nanocomposite rings.** *Adv Mater* 2008, **20**:4476-4481.
36. Sanchez T, Chen DTN, DeCamp SJ, Heymann M, Dogic Z: **Spontaneous motion in hierarchically assembled active matter.** *Nature* 2012, **491**:431-435.
37. Hoffmann C, Mazari E, Lallet S, Le Borgne R, Marchi V, Gosse C, Gueroui Z: **Spatiotemporal control of microtubule nucleation and assembly using magnetic nanoparticles.** *Nat Nanotechnol* 2013, **8**:199-205.
38. Wollman AJM, Sanchez-Cano C, Carstairs HMJ, Cross RA, Turberfield AJ: **Transport and self-organization across different length scales powered by motor proteins and programmed by DNA.** *Nat Nanotechnol* 2014, **9**:44-47.
39. Yashin VV, Balazs AC: **Pattern formation and shape changes in self-oscillating polymer gels.** *Science* 2006, **314**:798-801.
40. Maeda S, Hara Y, Sakai T, Yoshida R, Hashimoto S: **Self-walking gel.** *Adv Mater* 2007, **19**:3480-3484.
41. Maeda S, Hara Y, Yoshida R, Hashimoto S: **Peristaltic motion of polymer gels.** *Angew Chem Int Ed* 2008, **47**:6690-6693.
42. Shinohara S, Seki T, Sakai T, Yoshida R, Takeoka Y: **Photoregulated wormlike motion of a gel.** *Angew Chem Int Ed* 2008, **47**:9039-9043.
43. Lagzi I, Kowalczyk B, Wang DW, Grzybowski BA: **Nanoparticle oscillations and fronts.** *Angew Chem Int Ed* 2010, **49**:8616-8619.
44. Semenov SN, Wong ASY, van der Made RM, Postma SGJ, Groen J, van Roekel HWH, de Greef TFA, Huck WTS: **Rational design of functional and tunable oscillating enzymatic networks.** *Nat Chem* 2015, **7**:160-165.
- This paper shows that it is possible to modulate the properties of a biochemical oscillator in a rational manner and couple the oscillator to a chemical function.
45. Boekhoven J, Brizard AM, Kowligi KNK, Koper GJM, Eelkema R, van Esch JH: **Dissipative self-assembly of a molecular gelator by using a chemical fuel.** *Angew Chem Int Ed* 2010, **49**:4825-4828.
- This paper provides a first example of an entirely synthetic self-assembly process under dissipative conditions driven by chemical fuel. It is shown that the resulting material has a limited life time which depends on the amount of fuel present.
46. Boekhoven J, Hendriksen WE, Koper GJM, Eelkema R, van Esch JH: **Transient assembly of active materials fueled by a chemical reaction.** *Science* 2015, **349**:1075-1079.
47. Debnath S, Roy S, Ulijn RV: **Peptide nanofibers with dynamic instability through nonequilibrium biocatalytic assembly.** *J Am Chem Soc* 2013, **135**:16789-16792.
- The hybrid bio-synthetic approach for the transient self-assembly of gels shows the power of combining natural and synthetic components.
48. Pappas CG, Sasselli IR, Ulijn RV: **Biocatalytic pathway selection in transient tripeptide nanostructures.** *Angew Chem Int Ed* 2015, **54**:8119-8123.
49. Angulo-Pachon CA, Miravet JF: **Sucrose-fueled, energy dissipative, transient formation of molecular hydrogels mediated by yeast activity.** *Chem Commun* 2016, **52**:5398-5401.
50. Kumar M, Brocorens P, Tonnele C, Beljonne D, Surin M, George SJ: **A dynamic supramolecular polymer with stimuli-responsive handedness for in situ probing of enzymatic ATP hydrolysis.** *Nat Commun* 2014, **5**:5793.
51. Kumar M, Jonnalagadda N, George SJ: **Molecular recognition driven self-assembly and chiral induction in naphthalene diimide amphiphiles.** *Chem Commun* 2012, **48**:10948-10950.
52. Walde P, Umakoshi H, Stano P, Mavelli F: **Emergent properties arising from the assembly of amphiphiles. Artificial vesicle membranes as reaction promoters and regulators.** *Chem Commun* 2014, **50**:10177-10197.
53. Wang GT, Tang BH, Liu Y, Gao QY, Wang ZQ, Zhang X: **The fabrication of a supra-amphiphile for dissipative self-assembly.** *Chem Sci* 2016, **7**:1151-1155.
54. Maiti S, Fortunati I, Ferrante C, Scrimin P, Prins LJ: **Dissipative self-assembly of vesicular nanoreactors.** *Nat Chem* 2016, **8**:725-731.
- This paper describes the activation of building blocks by a chemical fuel relying on non-covalent interactions. The transient vesicular aggregates are able to sustain a chemical reaction as long as chemical fuel is present.
55. Pezzato C, Prins LJ: **Transient signal generation in a self-assembled nanosystem fueled by ATP.** *Nat Commun* 2015, **6**:7790.
56. Dambeniaks AK, Vu PHQ, Fyles TM: **Dissipative assembly of a membrane transport system.** *Chem Sci* 2014, **5**:3396-3403.
- A self-assembly process is described which is intrinsically dissipative. This implies that the collapse of the formed structure is caused by the structure itself, and does not rely on external factors such as enzymes or catalysts.
57. Chui JKW, Fyles TM: **Ionic conductance of synthetic channels: analysis, lessons, and recommendations.** *Chem Soc Rev* 2012, **41**:148-175.
58. Wood CS, Browne C, Wood DM, Nitschke JR: **Fuel-controlled reassembly of metal-organic architectures.** *ACS Cent Sci* 2015, **1**:504-509.
- This example sheds light on the potential of fuel-driven self-assembly processes for the time-controlled release of encapsulated molecules.
59. Fanlo-Virgos H, Alba ANR, Hamieh S, Colomb-Delsuc M, Otto S: **Transient substrate-induced catalyst formation in a dynamic molecular network.** *Angew Chem Int Ed* 2014, **53**:11346-11350.
- This paper describes the transient response of a complex chemical network to the addition of a fuel. The networks adapts spontaneously to form the structure best adapted to destroy the fuel and, afterwards, returns spontaneously to the resting state.